Karunaivel Kavipriya[1], Maria Lurdu Lavanya[2], Kuppusamy Bhuvaneswari[2], Veerapandian Velkannan[3], Nilavan Anitha[2], Susai Rajendran[2,4], Caslav Lacnjevac[5]*

[1]PSNA College of Engineering and Technology, Department of Chemistry, (Affiliated to Anna University, Chennai), Dindigul, India, [2]St. Antony's College of Arts and Sciences for Women, Department of Chemistry, Corrosion Research Centre, Dindigul-624005 (Affiliated to Mother Teresa Women's University, Kodaikanal, India), [3]Thiagarajar College of Engineering (Affiliated to Anna University, Chennai), Department of Chemistry, Thiruparankundram, Madurai, Tamil Nadu, India, [4]Pondicherry University, Centre for Nanoscience and Technology, Puducherry, India, [5]University of Belgrade, Faculty of Agriculture, Belgrade, Serbia.

Scientific paper
ISSN 0351-9465, E-ISSN 2466-2585
https://doi.org/10.5937/zasmat2203353K

Zastita Materijala 63 (3)
353 - 362 (2022)

Influence of a paint coating on the corrosion of hull plates made of mild steel in natural seawater

ABSTRACT

The corrosion resistance of mild steel (used to make hull plates in ship technology) in seawater before paint coating (Nippon paint, weatherbond advance) and after paint coating has been measured by electrochemical studies such as Polarisation study and AC impedance spectra. It is observed that after paint coating, the corrosion resistance of mild steel hull plates increases. Polarization study reveals that after paint coating, the linear polarization resistance increases and corrosion current decreases. AC impedance spectra reveal that in the presence of paint coating charge transfer resistance value increases, impedance value increases, phase angle increases and double layer capacitance value decreases.

Keywords: *paint coating, corrosion inhibition, hull plates, mild steel, natural seawater, electrochemical studies*

1. INTRODUCTION

Evaluation of leaf and bark extracts of Acacia tortilis as corrosion inhibitors for mild steel in seawater has been reported by Ali et al. Polarisation study reveals that the extracts act as mixed type inhibitors. AC impedance spectra confirm the formation of a protective layer on the metal surface. The adsorption of the inhibitors on the steel surface follow Langmuir adsorption isotherm model [1]. Ahmad et al. have reported synthesis, identification, theoretical and experimental studies for carbon steel corrosion inhibition in seawater for new urea and thiourea derivatives linkage to 5-Nitro Isatin Moiety. Isatin derivative is chosen as the best inhibitor by polarization study [2]. Influence of inhibitors on reinforced bar corrosion of coral aggregate seawater concrete has been investigated by Da et al.

The effect of inhibitors on corrosion behavior of reinforced bar in coral aggregate seawater concrete (CASC) in artificial seawater was studied by means of linear polarization resistance method (LPR) and electrochemical impedance spectroscopy (EIS). Two inhibitors, calcium nitrite rust inhibitor (CN) and amino-alcohol rust inhibitor (AA) are used. The effect of inhibitors on corrosion behavior of reinforced bar in coral aggregate seawater concrete (CASC) in artificial seawater was studied by means of linear polarization resistance method (LPR) and electrochemical impedance spectroscopy (EIS) [3]. Managing corrosion in desalination plants has been discussed by Schorr et al. To protect the desalination plant (DP) materials, industrial paints, polymeric coatings and rubber linings compatible with the DP fluids are applied. Cathodic protection with sacrificial anodic metals or impressed direct electrical current and corrosion inhibitors are supplied [4]. Corrosion studies of zinc coated steel parts in seawater have been made by Karthikeyan and Jeeva [5]. The corrosion inhibition of zinc coated steel sheets immersed in 3.5% NaCl with sulfisoxazole (SSZ) has been reported by weight

*Corresponding author: Karunaivel Kavipriya
Emai: susairajendran@gmail.com
Paper received: 05. 06. 2022.
Paper accepted: 16. 06. 2022
Paper is available on the website: www.idk.org.rs/journal

loss, potentiodynamic polarization, electrochemical impedance spectroscopy, hydrogen permeation studies and quantum mechanical studies.

Polarization studies confirmed that the inhibition mode follows a mixed type. The adsorption of the compounds onto the zinc coated steel surface obeyed Langmuir adsorption isotherm [5]. The corrosion inhibition of zinc coated steel sheets immersed in 3.5% NaCl with sulfisoxazole (SSZ) has been reported by weight loss, potentiodynamic polarization, electrochemical impedance spectroscopy, hydrogen permeation studies and quantum mechanical studies. Polarization studies confirmed that the inhibition mode follows a mixed type. Duduna et al. have compared various adsorption isotherm models for allium cepa as corrosion inhibitor on austenitic stainless steel in seawater. The sorption data of the allium cepa extract obeyed Langmuir, Freundlich, Temkin, El-Awady and Adejo Ekwenchi isotherm of which Langmuir Isotherm gave the best model fit [6]. In marine conditions, especially in the Arctic, the problems of reliability and safety of marine corrosion protection systems are relevant. Reliability can be enhanced by corrosion inhibitors. Phosphating compound with anode inhibitors have been used by Plaskeeva and Trusov [7]. Colloidal ZrO_2 nanoparticles have been used for corrosion protection of AA2024 in synthetic seawater by Elbasuney et al. Inhibition efficiency of 93.6% was achieved. It was noted that ZrO_2 could act as cathodic inhibitor by suppressing the dealloying of the intermetallic particles [8]. Shen et al. have made a Study of pitting corrosion inhibition effect on aluminum alloy in seawater by biomineralized film. The electrochemical results showed that the radius of the impedance arc of the alloy immersed in seawater with bacteria increased gradually with time. The bacteria promoted the formation of the $CaMg(CO_3)_2$ film, which blocked seawater from the alloy and consequently, inhibited pitting corrosion [9]. Xu et al. have investigated steel rebar corrosion in artificial reef concrete with sulphoaluminate cement. It has been observed that 2% dosage of corrosion inhibitor can significantly decrease the steel rebar corrosion in a new artificial reef concrete (NARC) to a similar corrosion degree of ordinary artificial reef concrete (ARC) [10]. The present work is undertaken to investigate the influence of a paint coating, namely, “Nippon paint, weatherbond advance” on the corrosion of hull plates made of mild steel in natural seawater, by electrochemical studies such as Polarisation study and AC impedance spectra.

2. EXPERIMENTAL WORK

Electrochemical studies

The corrosion resistance of mild steel (used to make hull plates in ship technology) in seawater has been measured by electro chemical studies such as Polarisation study and AC impedance spectra.

Polarisation study

A CHI electrochemical work station with impedance model 660A was used for this purpose. A three-electrode cell assembly electrode was used in the present study (Figure1). Mild steel was used as working electrode; saturated calomel electrode was used as reference electrode and Platinum electrode was used as counter electrode. From the Polarisation study corrosion parameters such as corrosion potential (E_{corr}) corrosion current (I_{corr}) and Tafel slope values (anodic = b_a and cathodic = b_c) and Linear polarisation resistance (LPR) were calculated. The scan rate (V/S) was 0.01. Hold time at (Efcs) was zero and quit times (s) was two.



Figure 1. Circuit diagram of three-electrode cell assembly

Slika 1. Šema sklopa ćelije sa tri elektrode

AC impedance spectra

AC impedance spectral studies were carried out on a CHI – Electrochemical workstation with impedance, Model 660A. A three – electrode cell assembly was used. The working electrode was mild steel, A saturated calomel electrode (SCE) was the reference electrode and platinum was the counter electrode.

The real part (Z') and imaginary part (Z'') of the cell impedance were measured in ohms at various frequencies. Values of the charge transfer resistance (Rt) and the double layer capacitance (Cdl), impedance value and phase angle were calculated from Nyguist plots and Bode plots.

Composition of mild steel

The composition of mild steel used in this study is given in Table1. This mild steel is used as hull plates in shipbuilding industry.

Table1. Composition of mild steel

Tabela 1. Sastav mekog čelika

Name	Average %	Abs. Std.Dev	Ref. Std.Dev	1	2
C	0.101	0.0014	1.4	0.102	0.1
Si	0.055	0.0021	3.89	0.053	0.056
Mn	1.629	0.0057	0.35	1.633	1.625
P	0.0087	0.0003	3.25	0.0085	0.0089
S	0.0028	0.0003	10.1	0.0026	0.003
Cr	0.036	0.0014	3.93	0.037	0.035
Mo	0.0086	0.00007	0.83	0.0086	0.0085
Ni	0.033	0.0007	2.18	0.033	0.32
Cu	0.0063	0.00007	1.13	0.0062	0.0063
Al	0.044	0.0014	3.21	0.043	0.045
As	0.0011	0	0	0.0011	0.011
B	0.0027	0.0005	18.68	<0.00010	<0.00010
Bi	<0.00010	0.00002	84.85	<0.0025	0.003
Ce	0.0032	0.0013	42.65	0.0041	0.0022
Co	0.011	0	0	0.011	0.011
Mg	0.0003	0	0	0.0003	0.0003
Nb	0.03	0.0007	2.4	0.029	0.03
Pb	0.0081	0.0013	15.71	0.0072	0.009
Sb	0.004	0.0004	8.95	0.0037	0.0042
Sn	0.0034	0	0	0.0034	0.0034
Ta	0.03	0.0071	23.57	0.025	0.035
La	0.0071	0	0	0.0071	0.0071
Ti	0.0035	0	0	0.0035	0.0035
V	0.138	0.0014	1.02	0.137	0.139
W	0.071	0,0078	11.03	0.076	0.065
Zn	0.0024	0	0	0.0024	0.0024
Zr	0.0051	0.0002	0.2	0.0052	0.0049
Se	<0.0005	0.0001	4.42	<0.0005	<0.0005
N	0.0093	0.00007	0.76	0.0092	0.0093
Ca	0.0014	0.0001	10.1	0.0013	0.0015
Te	0.0026	0.0025	97.91	<0.0010	0.0044
Fe	97.74	0	0	97.74	97.74

Seawater

The corrosion



Figure 8. Interactive 3 D-log freq plot of mild steel in seawater

Slika 8. Interaktivni 3 D-log freq dijagram mekog čelika u morskoj vodi



Figure 9. Nyquist plot of paint coated mild steel in seawater

Slika 9. Nyquist-ova kriva mekog čelika premazanog bojom u morskoj vodi



Figure 10. Bode plot of paint coated mild steel in seawater

Slika 10. Bode-ova kriva za meki čelik premazan bojom u morskoj vodi



Figure 11. Interactive 3D-log freq plot of paint coated mild steel in seawater

Slika 11. Interaktivni 3 D-log freq dijagram mekog čelika premazanog bojom u morskoj vodi

Based on the principles of the AC impedance spectra, it is inferred from Table 4 that in the presence of paint coating corrosion resistance of the hull plate made of mild steel in seawater increases. This is due to the fact that in the presence of paint coating, charge transfer resistance (R_t) increases, double layer capacitance (C_{dl}) decreases, phase angle increases and impedance value increases. The corrosion inhibition efficiency is 99.99%.

Implication

The hull plates made of mild steel may be coated with Nippon paint, weatherbond advance. This will control the corrosion of the hull plates in the seawater. It would lead to the increase in the lifetime of the hull plates.

4. CONCLUSIONS

The corrosion resistance of mild steel (used to make hull plates in shipbuilding technology) in seawater before paint coating (Nippon paint, weatherbond advance) and after paint coating has been measured by electrochemical studies such as Polarisation study and AC impedance spectra. It is observed that after paint coating, the corrosion resistance of mild steel hull plates increases. Polarization study reveals that after paint coating, the linear polarization resistance increases and corrosion current decreases. AC impedance spectra reveal that in the presence of paint coating charge transfer resistance value increases, impedance value increases, phase angle increases and double layer capacitance value decreases.

5. REFERENCES

[1] I.H.Ali, A.M.Idris, M.H.A.Suliman (2019) Evaluation of leaf and bark extracts of Acacia tortilis as corrosion inhibitors for mild steel in seawater: Experimental and studies, Int. J. Electrochem. Sci., 14(7), 6404-6419

[2] A.H.Ahmad, R.M.Kubba, S.M.Hussain Al-Majidi (2019) Synthesis, identification, theoretical and experimental studies for carbon steel corrosion inhibition in seawater for new urea and thiourea derivatives linkage to 5-Nitro Isatin Moiety, J. Global Pharma Tech., 11(7), 117-132

[3] B.Da, H.Yu, H.Ma, Z.Wu (2019) Influence of inhibitors on reinforced bar corrosion of coral aggregate seawater concrete, J. Chinese Soci. Corro. Protection, 39(2), 1152-159

[4] M.Schorr, B.Valdez, A.Eliezer, R.Salinas, C.Lora (2019) Managing corrosion in desalination plants, Corro. Reviews, 37(2), 103-113

[5] S.Karthikeyan, P.A.Jeeva (2019) Corrosion studies of zinc coated steel parts in seawater Portugaliae Electrochimica Acta, 37(5), 307-315

[6] W.E.Duduna, O.N.Akeme, T.M.Zinipere (2019) Comparison of various adsorption isotherm models for allium cepa as corrosion inhibitor on austenitic stainless steel in seawater Int.J.Sci.,Tech., Research, 8(8), 961-964

[7] E.Plaskeeva, V.Trusov (2019) Inhibited composition for work in marine conditions, E3S Web of Conferences, 121, 02011

[8] G.Elbasuney, M.Gobara, M.Zoriany, A.Maraden, I. Naeem (2019) Colloidal ZrO_2 nanoparticles for corrosion protection of AA2024, Environmental Nanotechnology, Monitoring and Management, 12, 100242

[9] Y.Dong, Y.Yang, L.Dong, J.Yin (2020) Study of pitting corrosion inhibition effect on aluminum alloy in seawater by biomineralized film Shen., Bioelectrochemistry, 132, 107408

[10] Q.Xu, T.Ji, Z.Yang, Y.Ye (2019) Steel rebar corrosion in artificial reef concrete with sulphoaluminate cement, Construction and Building Mater., 227, 116685

[11] S.C.Joycee, A.S.Raja, A.S.Amalraj, S.Rajendran (2021) Inhibition of corrosion of mild steel pipeline carrying simulated oil well water by Allium sativum (Garlic) extract, Int. J. Corro. Scale Inhib., 10(3), 943-960.

[12] R.Dorothy, T.Sasilatha, S.Rajendran (2021) Corrosion resistance of mild steel (Hull plate) in seawater in the presence of a coating of an oil extract of plant materials, Int. J. Corro. Scale Inhib., 10(2), 676-699.

[13] P.Shanthy, J.A.Thangakani, S.Karthika, S. Rajendran, J.Jeyasundari (2021) Corrosion inhibition by an aqueous extract of ervatamia divaricata, Int. J.Corro.Scale Inhib., 10(1), 331-348.

[14] S.J.H.M.Jessima, A.Berisha, S.S.Srikandan, S. Subhashini (2020) Preparation, characterization and evaluation of corrosion inhibition efficiency of sodium lauryl sulfate modified chitosan for mild steel in the acid pickling process, J. Molecular Liquids, 320,114382.

[15] M.E.Belghiti, Y.E.Ouadi, S.Echihi, F.Bentiss, A. Dafali (2020) Anticorrosive properties of two 3,5-disubstituted-4-amino-1,2,4-triazole derivatives on copper in hydrochloric acid environment: Ac impedance, thermodynamic and computational investigations, Surfaces and Interfaces, 21, 100692.

[16] A.S.Prabha, K. Kavitha, H.B. Shrine, S. Rajendran (2020) Inhibition of corrosion of mild steel in simulated oil well water by an aqueous extract of Andrographis paniculata, Indian J.Che.Tech., 27(6), 452-460.

[17] J.J.M.Praveena, J.A.Clara, S.Rajendran, A.J. Amalraj (2021) Inhibition of corrosion of mild steel in well water by an aqueous extract of soapnut (Sapindus Trifoliatus), Zastita Materijala, 62(4), 277-290.

[18] V.D.A.M.Jeslina, S.J.Kirubavathy, A. Al-Hashem, R. M.Joany, C.Lacnjevac (2021) Inhibition of corrosion of mild steel by an alcoholic extract of a seaweed Sargassum muticum, Zastita Materijala, 62(4), 304-315.

[19] S.Y.Al-Nami, A.S.Fouda (2020) Corrosion inhibition effect and adsorption activities of methanolic myrrh extract for cu in 2M HNO_3, Int. J. Electrochemical Sci., 15(2), 1187-1205.

[20] A.Ch. Catherine Mary, J.Jeyasundari, V.R. Nazeera Banu, S.S.Kumaran, A.P.Pascal Regis (2020) Corrosion behavior of orthodontic wires in artificial saliva with presence of beverage (Book Chapter), Nanotechnology in the Beverage Industry: Fundamentals and Applications, p.471-504.

[21] D.Kasapović, F.Korać, F.Bikić (2022) Testing the effectiveness of raspberry flower extract as an inhibitor of copper's corrosion in 3% NaCl, Zastita Materijala, 63(2), 115 - 121

[22] Al.Petričević, V. D.Jović, M.N.Krstajić Pajić, P. Zabinski, N.R.Elezović (2022) Oxygen reduction reaction on electrochemically deposited sub-monolayers and ultra-thin layers of Pt on (Nb-Ti)2AlC substrate, Zastita Materijala, 63(2), 153 - 164

[23] If.C.Ekeke, S.Efe, F.Ch.Nwadire (2022) Plant materials as green corrosion inhibitors for select iron alloys: a review, Zastita Materijala, 63(2), 183 - 202

[24] D.Rajendran, Th.Sasilatha, S.A.D.H. Mary, S.S. Rajendran, C.Lacnjevac, G.Singh (2022) Deep learning based underwater metal object detection using input image data and corrosion protection of mild steel used in underwater study - A case study, Part B - Corrosion protection of mild steel used in underwater study, Zastita Materijala, 63(1), 15 - 22

[25] D.Rajendran, Th.Sasilatha, S.S.Rajendran, Ab.Al-Hashem, C.Lacnjevac, G.Singh (2022) Inhibition of corrosion of mild steel hull plates immersed in natural seawater by sandalwood oil extract of some natural products, Zastita Materijala, 63(1), 23 - 36

[26] Vl.D.Jović (2022) Calculation of a pure double layer capacitance from a constant phase element in the impedance measurements, Zastita Materijala, 63 (1), 50 - 57

IZVOD

UTICAJ PREMAZA NA KOROZIJU PLOČA TRUPA OD MEKOG ČELIKA U PRIRODNOJ MORSKOJ VODI

Otpornost na koroziju mekog čelika (koji se koristi za izradu ploča trupa u brodskoj industriji) u morskoj vodi pre nanošenja boje (Nippon boja, vremenska veza unapred) i posle premaza boje je merena elektrohemijskim studijama kao što su studija polarizacije i spektri impedanse naizmenične struje. Primećeno je da se nakon nanošenja boje povećava otpornost na koroziju ploča trupa od mekog čelika. Studija polarizacije otkriva da nakon nanošenja boje, otpor linearne polarizacije raste a struja korozije opada. Spektri impedance naizmenične struje otkrivaju da se u prisustvu bojenog premaza vrednost otpora prenosa naelektrisanja povećava, vrednost impedanse povećava, fazni ugao raste i vrednost dvoslojne kapacitivnosti opada.

Ključne reči: *premaz boje, inhibicija korozije, ploče trupa, meki čelik, prirodna morska voda, elektrohemijske studije*

Naučni rad

Rad primljen: 05. 06. 2022.

Rad prihvaćen: 16. 06. 2022.

Rad je dostupan na sajtu: www.idk.org.rs/casopis

© 2022 Authors. Published by Engineering Society for Corrosion. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution 4.0 International license (https://creativecommons.org/licenses/by/4.0/)